



Zhejiang Shuntai Rubber And Plastic Technology CO., LTD.

Foaming agent (RA) testing report

Executive standard: Internal standard

Sampling location: RA workshop

Batch number: 2019071401

Sampling time: 07/15/2019

Analysis date: 07/15/2019

Style: SP7000

Quantity: 1000KGS

Item	Required indicator	Analysis result	Conclusion
Exterior	Light yellow powder	Light yellow powder	Pass
Decomposition temperature $^{\circ}\text{C} \geq$	200-220	218	Pass
Gas production (average) ML/g \geq	180-190	185	Pass
Average particle size D50um \leq	3-5	4.85	Pass
Reduced weight after heating \leq	0.1-0.15	0.1	Pass
Content % \geq	85-90	88	Pass
Ash %	0.25	0.12	Pass
PH \geq	6.5-7.5	7	Pass

Auditor: Hu Caizhen

Laboratory technician: Zhang

