



# Zhejiang Shuntai Rubber And Plastic Technology CO., LTD.

## Foaming agent (H) testing report

Executive standard: Internal standard

Sampling location: H workshop

Batch number: 2019072401

Sampling time: 07/25/2019

Analysis date: 07/25/2019

Style: Low temperature H-1

Quantity: 1000KGS

Item	Required indicator	Analysis result	Conclusion
Exterior	Light yellow powder	Light yellow powder	Pass
Decomposition temperature $^{\circ}\text{C} \geq$	150-170	160	Pass
Gas production (average) ML/g $\geq$	85-95	88	Pass
Average particle size D50um $\leq$	10-15	10.9	Pass
Moisture $\leq$ %	0.2	0.15	Pass
Content % $\geq$	40-50	46	Pass
Ash %	0.5	0.35	Pass
PH $\geq$	6.5-7.5	7	Pass

Auditor: Hu Caizhen

Laboratory technician: Zhang Y

