



**Zhejiang Shuntai Rubber And Plastic  
Technology CO., LTD.**

**Foaming agent (RA) testing report**

Executive standard: Internal standard

Sampling location: RA workshop Batch number: 2019071401

Sampling time: 07/15/2019 Analysis date: 07/15/2019

Style: RA-1 Quantity: 2000KGS

Item	Required indicator	Analysis result	Conclusion
Exterior	White powder	White powder	Pass
Decomposition temperature °C (start decomposition)	210	210	Pass
(end decomposition)	230	226	Pass
Gas production (average) ML/g $\geq$	120-130	128	Pass
Average particle size D50um $\leq$	10-15	10.4	Pass
Moisture % $\geq$	0.5MAX	0.21	Pass
Content % $\geq$	95	96	Pass
Ash %	0.5MAX	0.28	Pass
PH $\geq$	5-8	6.5	Pass

Auditor: Hu Caizhen

Laboratory technician Zhang Yi

