

## **Zhejiang Shuntai Rubber And Plastic Technology CO., LTD.**

## Foaming agent (AC) testing report

Executive standard: <u>Internal standard</u>

Sampling location: AC workshop Batch number: 2019071401

Sampling time: <u>07/15/2019</u> Analysis date: <u>07/15/2019</u>

Style: SA5000F Quantity: 2000KGS

Item	Required indicator	Analysis result	Conclusion
Exterior	Light yellow powder	Light yellow powder	Pass
Decomposition temperature °C (start decomposition)	150-160	156	Pass
(end decomposition)	190-200	190	Pass
Gas production (average) ML/g ≥	170-180	176	Pass
Average particle size D50um≤	6-8	7	Pass
Reduced weight after heating≤	0.1-0.15	0.1	Pass
Ash %	<b>≤</b> 2	0.15	Pass
РН ≽	7.5-8.5	8.1	Pass

Auditor: Hu Caizhen

Laboratory technician: