

Zhejiang Shuntai Rubber And Plastic Technology CO., LTD.

Foaming agent (AC) testing report

Executive standard: <u>HG/T2097-1991</u>

Sampling location: <u>AC workshop</u> Batch number: <u>2019071401</u>

Sampling time: <u>07/15/2019</u> Analysis date: <u>07/15/2019</u>

Style: SA3000 Quantity: 10000KGS

Item	Required indicator	Analysis result	Conclusion
Exterior	Light yellow powder	Light yellow powder	Pass
Decomposition temperature $^{\circ}\! {\Bbb C} \! \geqslant \!$	200-210	205	Pass
Gas production (average) ML/g ≥	210-220	218	Pass
Average particle size D50um≤	8-10	8.25	Pass
Reduced weight after heating ≤	0.1-0.15	0.06	Pass
content %≥	97-98	98	Pass
Ash %	0.1	0.07	Pass
РН ≽	6.5-7.5	6.5	Pass

Auditor: Hu Caizhen

Laboratory technician: Zha