



Zhejiang Shuntai Rubber And Plastic Technology CO., LTD.

Foaming agent (Expansion agent) testing report

Executive standard: Internal standard

Sampling location: Product warehouse Batch number: 2019071401

Sampling time: 07/15/2019 Analysis date: 07/15/2019

Style: ST-13 Quantity: 500KGS

Item	Required indicator	Analysis result	Conclusion
Exterior	White powder	White powder	Pass
Starting temperature °C \geq	145-155	146	Pass
End temperature °C \geq	185-200	195	Pass
Average particle size D50um \leq	25-50	45	Pass
Reduced weight after heating \leq	0.1-0.15	0.12	Pass
Ash %	\leq 0.1	0.1	Pass
PH \geq	6.5-7.5	7.1	Pass

Auditor: Hu Caizhen

Laboratory technician Zhang Yi

